

WIWAX POLYETHYLENE WAXES

WIRATEN XM-17

Parameter	Standard	Unit of measure	Requirement
Penetration at 25 °C	ASTM D 1321-16a	0,1 mm	2 – 5
Drop Point	ASTM D 3954-15	°C	99 - 105
Viscosity at 140 °C	ISO 3219:2000	cP	150 - 300
Acid Number	ASTM D 1386-15	mg KOH/g	15 - 19
Product form	Prills/Pastilles		