

WIWAX POLYETHYLENE WAXES

WIRATEN TWP-6

Parameter	Standard	Unit of measure	Requirement
Penetration at 25 °C	ASTM D 1321-16a	0,1 mm	< 2
Drop Point	ASTM D 3954-15	°C	105 - 120
Solidification Point	ASTM D 938-12	°C	98 - 106
Viscosity at 140 °C	ISO 3219:2000	cP	500 - 700
Product form	Prills/Pastilles		