PVC STRAIGHT HRTP2000H

Description

HRTP2000H, homopolymer made by suspension polymerization can be applied to extrusion and calendering process. it is used in products that require high mechanical properties and durability.
Suitable for high value products such as high-heat-resistant wire, abrasion resistance hose and flooring, high flexibility sheet, and gaskets.

Application

Wire & Cables, Automotive, Hose & tube Sheet & Tarpaullins

Properties	Method	Unit	PVC STRAIGHT HRTP2000H	Condition
Specification				
Particle size	LG Method PVC04	%	Max 0.05	45 Mesh
Degree of Polymerization	LG Method PVC03		1800 ~ 2200	
K-value			80	
Bulk Density	LG Method PVC01	g/cm³	0.390 ~ 0.450	
Density			1.4	23℃
Volatiles	LG Method PVC02	%	Max 0.3	

Issued Date : 2026-01-07

The information contained herein, including, but not limited to, data, statements and typical values, are given in good faith. LG Chem makes no warranty or guarantee, expressed or implied, (i) that the result described herein will be obtained under end - use conditions, or (ii) as to the effectiveness or safety of any design incorporating LG Chem materials, products, recommendations or advice. Further, any information contained herein shall not be construed as a part of legally binding offer. Especially, the typical values should be regarded as reference values only and not as binding minimum values. Each user bear full responsibility for making its own determination as to the suitability of LG Chem's materials, products, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating LG Chem material or products will be safe and suitable for use under end - use conditions. The data contained herein can be changed without notice as a result of the quality improvement of the products.