SolutionPartner

LG Chem

MB838A

Opaque impact modifier

Description

Opaque & high impact performance

Application

Sheet, Pipe, Fitting etc

Powder Characteristics		Unit	Specification	REF. Method
Bulk density	Aerated	g/cc	Min. 0.32	LSY-QB-KD019
Size distribution	#20 mesh on	Wt%	Max. 3.0	LSY-QB-KD018
	#200 mesh pass	Wt%	Max. 20	
Volatile material		Wt%	Max. 1.0	ISO 1625
Foreign material		Number (10 ×10 ㎝)	Max. 3	LSY-QB-KD005
Mechanical Characteristics				
Rotary impact strength		%	Min. 65	LSY-QB-KD023
Izod impact strength	23℃	㎏ ㎝/㎝	Min. 100	ISO 180
Other				
Fusion time		sec	40 ~ 60	ISO 1830-6

* For more information. Please kindly contact us. (Add : LG Twin Towers 20, Yoido-dong, Seoul 150-606, Korea
Tel : 82-2-3773-7749, Fax : 82-2-3773-7660)

본 문서는 지정된 수신인만을 위한 것이며, 부정경쟁방지 및 영업비밀의 보호에 관한 법률을 포함하여 관계 법령에 따라 보호의 대상이 되는 영업비밀 등을 포함하고 있을 수 있습니다. 본 문서에 포함된 정보의 전부 또는 일부를 무단으로 제3자에게 공개, 배포, 복사 또는 사용하는 것은 엄격히 금지되며, 경우에 따라 민, 형사상 책임을 질 수 있습니다. 본 문서가 잘못 전달된 경우, 발신인 또는 당사에 알려 주시고, 본 문서를 즉시 파쇄 폐기하여 주시기 바랍니다. ㈜LG화학
The information contained herein is intended for the named recipients only. It may contain privileged and confidential Information or otherwise protected under applicable laws. If you have received this document in error, please immediately notify The sender and shred the documents and any attachments without any copying or disclosure of the contents. LG Chem, Ltd.