

# MB875

Transparent impact modifier

## Description

Transparency, general purpose

## Application

Transparent sheet, film etc

Characteristics		Unit	Specification	REF. Method
Appearance			White powder	
Bulk density	Aerated	g/cc	Min. 0.32	ASTM D1895
Size distribution	#20 mesh on	wt%	Max. 3.0	ASTM D1921
Volatile material		wt%	Max. 1.0	ISO 1625
Foreign material		Point	Max. 3	LSY-QB-KD005

- For more information, please kindly contact us.
- Address : LG Twin Towers, 128, Yeouidaero, Yeongdeungpo-gu, Seoul, Korea, 150-721
- Tel : 82-2-3773-7749, Fax : 82-2-3773-7660

The information contained herein, including, but not limited to, data, statements and typical values, are given in good faith. LG Chem makes no warranty or guarantee, expressed or implied, (i) that the result described herein will be obtained under end-use conditions, or (ii) as to the effectiveness or safety of any design incorporating LG Chem materials, products, recommendations or advice. Further, any information contained herein shall not be construed as a part legally binding offer. Especially, the typical values should be regarded as reference values only and not as bidding minimum values. Each user bear full responsibility for making its own determination as to the suitability of LG Chem's materials, products, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analysis necessary to assure that its finished parts incorporating LG Chem material or products will be safe and suitable for use under end-use conditions. The data contained herein can be changed without notice as a result of the quality improvement of the products.

Copyright© 2010 LG Chem. All right reserved